



VK-M54

FLOOR PRODUCTS

Technical Data Sheet

Revised: 04/2021

DESCRIPTION

Adhesive in water dispersion. Suitable for all types of PVC, cork flooring with PVC backing, textile flooring (with latex back and PU foam) and linoleum, linoleum with back in natural and synthetic jute and action back (polypropylene), with back poliefine and PU. Also suitable for LVT, VCT and needle punched floors.

- + Fast setting
- + Strong initial tack
- + Low C.O.V (Volatile Organic Compounds)
- + Antibacterial and anti-mold properties

Suitable for:

- PVC coverings
- linoleum
- homogeneous PVC wall coverings
- needle punch floorings and fiber bonded carpets with PU supports
- natural cork coverings and PVC-backed floor coverings
- thermal and absorbent coatings

SURFACE PREPARATION

All surfaces must be dry, absorbent, strong, free of dust or paints or oils. Any cracks or holes must be covered with our extra-light GLASTER and in case of imperfections shaved with a normal stucco plaster.

We always recommend the use of our PRIMER AC fixative for consolidation and cleaning.

We recommend using our PRIMER SP (specific for wet floors with fungi and mold) in case of rising damp or too humid areas.

COATING PREPARATION

Before to proceed with the application we recommend to put the material at the construction site the day before in order to allow an adaptation to the temperatures of the environment of laying.

Follow the temperature advises given by the manufacturer.

Unroll or simply unpack the floorings in order to decrease tensions and folds.

PRODUCT PREPARATION

VK-M54 is ready to use product however, when necessary, dilute it with clean water up to a maximum of 5%.

APPLICATION

Apply the adhesive in a single coat with a roller or a notched trowel No. 2.

ROLLER - Apply the product directly on the surface with roll short wool for about 10/15 m². Proceed accordingly to the application of the wall covering.

Video tutorial: <https://www.youtube.com/watch?v=2p-pteh2B1Y>

SPATULA - Apply undiluted with a notched trowel No. 2 directly on the surface. Then proceed to the preparation of materials.

CONSUMPTION

250 - 350 g/m²

CLEANING

We recommend to clean the joints and excess adhesive with a wet sponge. Any adhesive spillage must be removed immediately. The product does not stain.

CONTRAINDICATIONS

VK-M54 is not suitable for non-absorbent surfaces, damp floors with mold or on surfaces that are not perfectly prepared.

PACKAGES

bucket 6 Kg
bucket 13 Kg
bucket 20 Kg

code 20112
code 20113
code 20109

STORAGE

The product is guaranteed for 24 months from the date of production. Preserve from frost. (+ 5 °C + 40 °C)

TECHNICAL DATA PRODUCT

base:	water
appearance:	cream beige
pH:	6.8
viscosity:	25,000 to 35,000 cps
percentage of solid:	70%
customs code:	3506 9100
application temperature:	+ 5 °C + 40 °C
waiting time:	10 - 15 minutes
open time:	20-30 minutes
setting time:	24 hours
not flammable	

FINAL PROVISIONS

Keep out of the reach of children and pets. Discharge the waste in special containers for building materials.



ACM Italy S.r.l. | Via Enrico Mattei, 8 | 20010 Casorezzo /MI
PHONE +39 02 903 611 48 | laboratorio@acm-italy.com | www.acm-italy.com