



# ADHESIVA 2PG

## TWO-COMPONENT STRUCTURAL EPOXY-POLYURETHANE ADHESIVE



TECHNICAL DATA SHEET UPDATED 11/02/2026

### Product Information

Two-component epoxy-polyurethane structural adhesive (A+B), ideal for bonding rubber floors, resilient and sports flooring both indoors and outdoors, as well as any type of prefinished or solid wood parquet.

- + Solvent-free
- + Low shrinkage
- + Strong adhesion

### Recommended Uses

- Rubber flooring in tiles or sheets exposed to heavy traffic
- Vinyl flooring on cement, marble, or ceramic
- Rubber flooring (also natural) with smooth or rough backing, even outdoors
- Synthetic grass
- Prefinished parquet
- Multilayer parquet
- Solid wood parquet of any thickness

### Coverage

800 - 1000 g/m<sup>2</sup>

### Application Instructions

#### Substrate Preparation

All substrates must be dry, absorbent, resistant, and free from dust, paint, or oil. Any cracks should be sealed using our EPOXY ECO two-component adhesive.

For uneven surfaces, we recommend applying a powder-based leveling compound such as our SELF LEVEL FLOORING (Suprimo line) or the ready-to-use TILECOAT.

To consolidate and clean the surface, use our PRIMER SP. In case of moisture rising or very humid substrates, use PRIMER PU.

#### Covering Preparation

We recommend bringing the covering to the job site the day before installation to allow it to acclimate. Install the floor following the manufacturer's temperature guidelines. Unroll or unpack the flooring to reduce tension or folds.

#### Product Preparation

Pour component B (hardener) into component A (base resin in large bucket) and mix thoroughly until a uniform color is achieved. Use a low-speed electric mixer for about 5 minutes.



# ADHESIVA 2PG

TWO-COMPONENT STRUCTURAL  
EPOXY-POLYURETHANE  
ADHESIVE



TECHNICAL DATA SHEET UPDATED 11/02/2026

## Product Application

Apply the mixed adhesive with a medium-toothed trowel (No. 2/3) directly onto the floor. Place the covering ensuring complete contact with the adhesive layer.

## Cleaning

Clean tools with nitro thinner before the product cures.

Packaging	PRODUCT CODE	WEIGHT	UNIT	PACKAGING	PCS/BOX
	20047-5-N	5	kg	Bucket	1
	20048-10-N	10	kg	Bucket	1

Technical Data	Base	Epoxy-polyurethane
	Physical appearance	Beige cream (custom colors on request)
	Mixing ratio	9:1
	Solids content	Approx. 60%
	Customs code (A+B)	3909 5090
	Application temperature	+10°C to +35°C
	Waiting time	None
	Open time	Approx. 60 minutes
	Walkable after bonding	12–24 hours
	Full cure	48 hours

## Warnings

- Do not use at temperatures below +10°C
- Recommended application between +10°C and +35°C
- Non-absorbent surfaces must be treated to make them porous



# ADHESIVA 2PG

TWO-COMPONENT STRUCTURAL  
EPOXY-POLYURETHANE  
ADHESIVE



TECHNICAL DATA SHEET UPDATED 11/02/2026

---

## Storage

The product is guaranteed in its original packaging, under standard storage conditions (+5 °C to +35 °C / +41 °F to +95 °F), for 18 months from the production date. It is important to store the product in a dry place, away from heat sources and direct sunlight.

---

## Final note

Keep out of reach of children and pets. Dispose of waste in designated construction material containers.

The information in this technical sheet is based on our extensive experience but is indicative. Users must assess product suitability for their specific use and are responsible for its application.

---