

# **TECHNICAL DATA SHEET**

REVISED: 19/09/2023

## **ADHESIVA SBR**

### **SEALANTS AND MOUNTING**



Single component SBR (Styrene Butadiene Rubber) water based rubber adhesive, for bonding structural building elements and thermo-acoustic absorbent materials. High adhesion on low absorbent surfaces, elastic-strong adhesion.

Suitable for:

- Structural construction materials
- Wood, PVC and ceramic baseboard applications
- Tiles, Ceramics and Polyurethane applications
- Polystyrene and polyurethane panels, frames and rosettes
- Cork and thermo-acoustic materials
- Thermo-insulation boards
- PVC skirting board

#### **TECHNICAL FEATURES:**

- + Fast drying
- + Strong initial tack
- + Thixotropic behaviour
- + Solvent free
- + No shrinkage
- + No nails support required
- + Strong suction cup effect

#### **SURFACE PREPARATION**

All surfaces must be dry, absorbent, strong, free of dust, paints or oils. Any cracks or holes in the wall must be covered with our extra-light filler GLASTER.

#### **ADHESIVE PREPARATION**

Mono-component adhesive and ready-to-use. Cut the seal of the cartridge and use a special caulking gun for cartridges

#### **APPLICATION**

Apply the product all over the contact surface.

#### **CONSUMPTION**

- 200 – 300 g/m<sup>2</sup> when applied by trowel
- about 20 m (linear) per cartridge

#### **CLEANING**

Clean the equipment with fresh water immediately after use, or remove mechanically.

#### **CONTRAINDICATIONS**

- Do not use at temperatures below +3 °C
- Application is recommended between +10 °C and +35 °C

---

[www.acm-italy.com](http://www.acm-italy.com)

# TECHNICAL DATA SHEET

REVISED: 19/09/2023

## **ADHESIVA SBR**

### SEALANTS AND MOUNTING



#### PACKAGING

PRODUCT CODE	WEIGHT	UNIT	TYPE OF PACKAGING	PCS IN BOX
30002	300	ml	cartridge	24
30003	6	kg	bucket	1

#### STORAGE

The product is guaranteed in its original packaging, in standard conditions (+5 °C to + 35 °C), for 24 months from date of production. It is important to keep the product in dry conditions, away from heat sources and direct sunlight.

#### PRODUCT TECHNICAL DATA

Base	Water -SBR
Appearance and colour	Brown light-dark
Solids percentage	about 80%
Customs code	3506 9100
Application temperature	+10°C +35°C
Setting time	10-15 min
Open Time	About 30-40 min
Drying time	48 hours

#### FINAL REGULATIONS

Keep out of reach of children. Discharge the waste in special containers for building materials

#### DISCLAIMER

The above mentioned information and prescriptions, even if they correspond to our best experience are purely indicative and must be confirmed by practical applications. Therefore before using, it is necessary to establish if it fits the prescribed use and the final customer assumes any responsibility that may derive from its use.