



VICEVERSA COAT MIRROR



TWO-COMPONENT TRANSPARENT
EPOXY PROTECTIVE COATING

UPDATED DATA SHEET 17/04/2025

Product information

Two-component transparent epoxy protective coating, specifically designed for the lacquering of resin wall coverings and flooring. Provides surfaces with high resistance to scratches and wear, while making them easy to clean. Ideal for both residential and commercial environments.

- + High gloss
- + Crystal-clear transparency
- + Does not alter substrate color
- + Non-staining
- + Non-yellowing
- + Solvent-free

Suggested Applications

- Finish for resin flooring
- Exterior wall coatings
- Self-leveling lacquers

Product yield

- 2.2 kg/m² for a thickness of 2 mm
 - 1.2 kg/m² for a thickness of 1 mm
- Coverage may vary depending on the type of substrate, application method, and environmental conditions.

Application Guidelines

Surface preparation

Make sure the surface to be treated is completely dry, clean, and free of dust, grease, or moisture.

Do not apply in environments with residual humidity or at temperatures below 12°C (53.6°F).

If applying near windows or direct sunlight sources, it is recommended to mask the glass surfaces for at least 2–3 days after application to avoid surface curing issues.

Product preparation

Mix Part A and Part B thoroughly in a 100:60 weight ratio (e.g., A = 1.0 kg + B = 0.6 kg), using a low to medium speed drill mixer until a homogeneous mixture is obtained.

Use the product within 15–20 minutes of mixing to avoid thickening and loss of workability.



VICEVERSA COAT MIRROR



TWO-COMPONENT TRANSPARENT
EPOXY PROTECTIVE COATING

UPDATED DATA SHEET 17/04/2025

Product Application

Slowly pour the mixed product onto the surface and spread it using a smooth or notched trowel, depending on the desired finish.

To help eliminate air bubbles, spray VICEVERSA PU COAT DILUENT within 5–10 minutes after application.

Cleanliness

Clean tools with water while the product is still fresh, or remove them mechanically once the product has dried.

Product Technical Data

Color	Comp. A transparent / Comp. B transparent
Base	Two-component epoxy
Finish	High gloss (imperceptible to the touch)
Physical appearance	Liquid (both A and B)
Density (g/L)	1100
Solids content	100%
Pot life at 20°C	25/30 minutes
Walkable at 20°C	32 hours
Touch dry at 20°C	16 hours
Minimum application temperature	+12°C
Full curing	7 days
Elastic modulus	1850 mPa
Elongation at break	8%
Compressive strength	300 Kg/mm ²

ACM Italy S.r.l.

Viale Enrico Mattei, 8 - 20010 Casorezzo (Milan), Italy

+39 02 90361148 | info@acm-italy.com

www.acm-italy.com



VICEVERSA COAT MIRROR



TWO-COMPONENT TRANSPARENT
EPOXY PROTECTIVE COATING

UPDATED DATA SHEET 17/04/2025

Contraindications

Do not use in the presence of moisture.
Avoid direct exposure to sunlight during application.
Wait at least 7–10 days, depending on ambient temperature, before placing furniture or heavy objects on the treated surfaces.

Final provisions

Keep out of reach of children and pets.
Dispose of waste in designated construction material containers.

Preservation

The product, in its original packaging and under standard conditions (+5°C / +35°C | 41°F / 95°F), is guaranteed for 12 months from the date of manufacture.
It is essential to store it in a dry place, away from sources of heat and direct sunlight, to preserve its properties and shelf life.

Warnings

The information provided in this Technical Data Sheet is based on our long-standing experience but is intended as a guideline. Therefore, the user must assess whether the product is suitable for their specific application and takes full responsibility for its use.