



VICEVERSA COAT MIRROR

TWO-COMPONENT TRANSPARENT
EPOXY PROTECTIVE COATING



UPDATED DATA SHEET 25/05/2026

Product information

Two-component transparent epoxy protective coating, specifically developed for the coating of wall coverings and resin flooring. It provides surfaces with high resistance to scratches and wear, while making them easy to clean. Ideal for both residential and commercial environments.

- + Extra glossy
- + Absolute transparency
- + Does not alter the colour of the substrate
- + Non-staining
- + Non-yellowing
- + Solvent-free

Suggested Applications

- Finishing of resin flooring
- Exterior wall coverings
- Self-levelling clear coatings

Product yield

- 2.2 kg/m² for a thickness of 2 mm
 - 1.2 kg/m² for a thickness of 1 mm
- Coverage may vary depending on the type of substrate, application method, and environmental conditions.

Application Guidelines

Substrate preparation

Ensure that the surface to be treated is perfectly dry, clean, and free from dust, grease, or moisture.

Do not apply in environments with residual humidity or at temperatures below 12°C.

When applying near glass surfaces or in areas exposed to direct sunlight, it is recommended to mask glass surfaces for at least 2–3 days after application to avoid surface curing issues.

Product preparation

Thoroughly mix Part A and Part B in a 100:60 weight ratio (e.g. A = 1.0 kg + B = 0.6 kg), using a mixing drill at medium–low speed until a homogeneous mixture is obtained.

Use the product within 15–20 minutes after mixing to prevent thickening and loss of workability.

Product Application

Apply the product with a microfibre flat paint roller or with a spatula, depending on the type of application.

To help eliminate air bubbles, spray VICEVERSA PU COAT DILUENT within 5–10 minutes after application.



VICEVERSA COAT MIRROR

TWO-COMPONENT TRANSPARENT
EPOXY PROTECTIVE COATING



UPDATED DATA SHEET 25/05/2026

Cleaning

Clean tools with water while the product is still fresh, or remove residues mechanically once the product has cured.

Product Technical Data

Colour	Comp. A transparent / Comp. B transparent
Base	Two-component epoxy
Finish	Extra glossy (imperceptible to the touch)
Physical appearance	Liquid (both A and B)
Density	1100 g/L
Solids content	100%
Pot life at 20°C	25–30 minutes
Light foot traffic at 20°C	32 hours
Touch dry at 20°C	16 hours
Minimum application temperature	+12°C
Full curing	7 days
Elastic modulus	1850 MPa
Elongation at break	8%
Compressive strength	300 kg/mm ²

Contraindications

- Do not use in the presence of moisture.
- Avoid direct exposure to sunlight during application.
- Wait at least 7–10 days, depending on ambient temperature, before placing furniture or heavy objects on treated surfaces.

Final provisions

Keep out of reach of children and pets.
Dispose of waste in designated construction material containers.



VICEVERSA COAT MIRROR

TWO-COMPONENT TRANSPARENT
EPOXY PROTECTIVE COATING



UPDATED DATA SHEET 25/05/2026

Preservation

Store the product in its original, tightly closed packaging, in a cool, dry, and well-ventilated environment, away from heat sources, frost, and direct sunlight. Storage temperature must be between +5°C and +35°C.

Under these conditions, the product retains its characteristics for 12 months from the production date. Protect from moisture and contamination.

Warnings

The information provided in this Technical Data Sheet is based on our long-standing experience but is intended as a guideline. Therefore, the user must assess whether the product is suitable for their specific application and takes full responsibility for its use.